

## Data Sheet

# SENTINEL ROOFING TOPCOAT

### Advantages

- Great cost/performance ratio
- Satin aspect
- Available in many colours
- Anti-bubbles included
- Easy to use
- Easy to sand
- Low styrene content
- Good covering power

### Technical Specifications

<b>Ref.</b>	GCTC-522
<b>Spray</b>	
<b>Brush</b>	X
<b>Static viscosity(cps)</b>	17000 - 25000
<b>Density</b>	1.25
<b>Thixotropy</b>	2,5-4
<b>Gel time (minutes)*</b>	10-20

### Application

This product must be used at workshop temperature between 15 and 30 °C

#### Mix before using.

No dilution is requested, only add the catalyst.

Catalyze: between 1 and 2.0% of MEKP 50, according to the requested thickness and production cycle. It is possible to use low reactivity catalysts.

For spraying we advise a nozzle of 18 to 31 with a 40 to 60 degree max spray angle.

It is recommended to cross passes at more than 50 centimetres from the mold.

We recommend applying a thickness of minimum 500 microns.

Possible to apply up to 800 microns in several passes.

Do respect security procedures.

Please contact us for further information.

#### Storage Conditions:

Product should be kept away from direct sunshine and at temperature below 20 °C. Under these conditions, the product will keep its properties 4 months from receiving date.

The information contained in this technical data sheet reflects our current knowledge. It aims at providing information about the application possibilities.

*As we cannot control the applications' condition, we cannot be held responsible beyond the providing of material in accordance without specifications*